

# HydraTech ACID HYDRAWRAP SYSTEM

Issue 2.09

# HydraTech Acid HydraWrap System

- HydraWrap is FRP repair system engineered to restore or enhance the structural integrity of pipe and infrastructure.
- Each HydraWrap system is a uniquely designed high performance Carbon Fiber Reinforced Polymer (CFRP) Composite that consists of a 100% solids high build epoxy Primer, a 100% solids epoxy Wet-Out resin, and carbon fiber fabric.
- The Primer provides excellent adhesion to a variety of substrates while allowing a sag free application at high film builds.
- The Wet-Out resin is designed to thoroughly wet out the fiber forming a composite matrix with a very high tensile and flexural properties.
- The Acid HydraWrap system is designed to exceed the Standard HydraWrap in applications where the HydraWrap will come in contact with aggressive acids and reagents.

#### **ADVANTAGE**

- Rapid development of physical properties with ambient cure. No post cure required.
- Chemical and Corrosion Resistant Structural Repair
- High Tensile / Flexural Modulus and Strength
- 100% Solvent-Free, Zero V.O.C.
- Low temperature cure down to 40°F (4°C).
- Restores Maximum Allowable Operating Pressure (MAOP)
- Installed by fully trained application specialists
- Full contract support services available

The **HydraTech HydraWrap** system is a performance driven product that provides a chemical and corrosion resistant structural repair for infrastructure and the interior or exterior of pipe. The HydraWrap system is backed by our engineering staff that services each application with assessment and technical support. The HydraWrap system offers a low cost, long term solution to the most challenging demands of the industry.



### **PROPERTIES**

	<u>Primer</u>	Wet-Out
Color	Steel Green	Clear
Working Life - 68°F (20°C)	15 minutes	15 minutes
Dry Times – 68°F (20°C)	4 Hours	4 Hours
% Vol Solids (ASTM 2369)	100	100
Shore D Hardness (ASTM D224	0) 80	85

Mix Ratio - Pre-measured 1:1 Flash Point - > 200°F (93°C)

Storage Life - Twelve months when stored in original sealed containers, between 50-77°F (10-25°C)

### **PERFORMANCE DATA**

Composite System (two ply bidirectional)	Hoop 200C	Hoop 300C	Axial 300C
Tensile Strength ASTM D3039 (ksi)	53.7	100	16.8
Tensile Modulus ASTM D3039 (msi)	4.36	8.67	2.3
% Elongation ASTM D3039	1.27	1.12	0.77
Flexural Strength ASTM D790 (ksi)	60	87.3	22.97
Flexural Modulus ASTM D-790 (msi)	3	4.9	1.21
ASTM E831 (x10-6/°F)		13.2	
Thermal Cycling ASTM D6944 ( 0-200°F)	>30		
Maximum Operating Temperature (°F)	200	200	200

Conforms to DOT regulations • PCC-2 Art 4.1, 4.2 • ASME B31.1•.3•.4•.8 • API 570 • ISO15649 • ISO13623 • ACI 440.2R08

For details regarding the testing associated with the provided data refer to the HydraWrap Testing and Design Sheet.

### SUBSTRATE PREPARATION

Substrate preparation dictates the adhesion performance of any coatings system. A properly prepped surface will ensure maximum life and performance of the system.

Concrete: NACE No.6\* / SSPC-SP13\*

Steel: NACE No.2\* / SSPC-SP 10\*

NACE No.3 / SSPC-SP 6 NACE No.5 / SSPC-SP 12 \*indicates recommended method



## **PERFORMANCE DATA**

### **CHEMICAL RESISTANCE** ASTM D543 (30 day immersion)

Water	No Effect
Sodium Hydroxide 5%	No Effect
Ammonium Hydroxide 5%	No Effect
Sodium Hypochlorite (bleach)	No Effect
Ferric Chloride 1%	No Effect
Sulfuric Acid 98%	Discoloration
Nitric Acid 1%	No Effect
Detergent Solution	No Effect
Gasoline	No Effect
Toluene	No Effect
Phosphoric Acid 50%	No Effect
Hydrochloric Acid 36%	Discoloration

### **ADHESION** ASTM D4541 (24Hr cure)

Cold Rolled Steel	>2,000 psi
Hot Rolled Steel	>2,000 psi
Cast Iron	>2,000 psi
304 Stainless Steel	>2,000 psi
316 Stainless Steel	>2,000 psi
Concrete	Concrete Failure

## **APPLICATION REQUIREMENTS**

Minimum Application Temp. 40°F (4.4°C)

Maximum Relative Humidity 85%

Note

Substrate Temperature 5°F (3°C) above dew point

Thinning Do not thin

Cleaning Fluid Universal Equipment Cleaner

To aid application at low

temperatures, both components should be warmed to 60-68°F (15.5-20°C) prior to mixing.

#### INSTALLATION PROCEDURE

- Prep substrate according to NACE / SSPC spec.
- Measure fabric around pipe to ensure proper length.
- Mechanically mix together both primer components until uniform.
- Apply primer to prepared substrate via brush or spreader.
- Mix both Wet-Out components for two minutes.
- Apply Wet-Out to fabric via spreader or impregnator ensuring complete wet out of fabric.
- Apply saturated fabric to wet primer ensuring a consistent, smooth wrap free of voids.
- Allow system to completely cure.
- If exposed to sunlight, top coat the wrap with a light stable top coat.

For details regarding application refer to the HydraWrap Installation Procedure

#### NOTE

The **HydraTech** Acid **HydraWrap** System is not intended for applications with exposure to strong acids, organic acids, strong solvents (MEK, Acetone, Alcohol) at elevated temperatures. Consult technical staff regarding applications where exposure to organic acids or strong solvents may exist. To be applied by certified personnel only. See MSDS for safety information.

	Unit Size	Coverage
PRIMER	Pt	<b>4.5</b> sqft
	Qt	9 sqft
	Hg	<b>23.5</b> sqft

WET-OUT

Pt	4 sqft of fabric
Qt	8 sqft of fabric

(Primer coverage based on 32mil film build. Wet-Out coverage based on 99.36g/sqft of 300C fabric.)

## **ORDER INFORMATION**

Part No. for standard kits consist of: System Code - Pipe Size - Pipe Style ex. SH-12-W (STD HydraWrap for 12" Weld Repair)

System Code	Pipe Size		Pipe Style
SH – Standard HydraWrap	4 – will wrap up to one 4" pipe	12 – will wrap up to one 12" pipe	W – Weld
HH – High Temp HydraWrap	6 – will wrap up to one 6" pipe	16 – will wrap up to one 16" pipe	E – Elbow
AH – Acid Resistant HydraWrap	8 – will wrap up to one 8" pipe	18 – will wrap up to one 18" pipe	T – Tee
PH – Potable Water HydraWrap	10 – will wrap up to one 10" pipe	24 – will wrap up to one 24" pipe	SS –Strait Spiral

Custom kits are supplied to accommodate nearly any installation